

CLIENT:

Company:	Turf Distributors
Address:	42505 Rionedo Road Temecula, CA 92590
Requested By:	Dillon Georgian

TEST MATERIAL:

Date Material Received:	April 14, 2020
Material Type:	Synthetic Turf
Material Condition:	Excellent, New
Material ID:	Eco 94 Gold

TESTING METHODS REQUESTED:

<i>Testing Services Inc. was instructed by the client to test for the following...</i>			
Standard:	ASTM D1335	Test Method:	Standard Test Method for Tuft Bind Strength of Pile Yarn Floorcoverings

SAMPLING PLAN:

Sampling Date:	4/14/2020
<ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested 	

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.
None


TEST SUMMARY:

TEST METHOD	TEST DESCRIPTION		TEST RESULT							
ASTM D1335-17e1	Average Tuft Bind Strength		10.4 lbs/force							
➤ Each individual pull was made on a combination of Monofilament fibers and textured fibers, same needle site										
Pull #1	11.41 lbs/force	Pull #2	10.66 lbs/force	Pull #3	12.35 lbs/force	Pull #4	9.315 lbs/force	Pull #5	10.36 lbs/force	
Pull #6	9.584 lbs/force	Pull #7	9.074 lbs/force	Pull #8	11.11 lbs/force	Pull #9	10.87 lbs/force	Pull #10	8.456 lbs/force	
Pull #11	11.41 lbs/force	Pull #12	9.262 lbs/force	Pull #13	9.906 lbs/force	Pull #14	9.906 lbs/force	Pull #15	12.94 lbs/force	

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

Test Report Approval:

 Digitally signed by Erle Miles
 DN: cn=Erle Miles, o=Testing Services Inc. Inc.
 email=erle@testing-services-usa.com, c=US
 Date: 2020.10.10 08:40:04 -0400' Erle Miles, III, Lab Director Testing Services (TSI) LLC

TSi Accreditation: Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0. TSi is an Organizational Member of ASTM (American Society for Testing and Materials). TSi is a certified independent testing laboratory by the STC (Synthetic Turf Council).



Testing Services (TSI) LLC
 817 Showalter Avenue
 PO Box 1343
 Dalton, GA 30721