

LABORATORY TEST REPORT

Report # 81001B-01 Lab Test Number: **Report Date:**

3192-3349 August 14, 2020

ASTM D1335 Tuft Bind

www.testingservices-usa.com • (706)226-1400

office@testingservices-usa.com

CLIENT:

Company: Turf Distributors					
Address: 42505 Rionedo Road					
	Temecula, CA 92590				
Requested By:	Dillon Georgian				

TEST MATERIAL:

Date Material Received:	April 14, 2020			
Material Type:	Synthetic Turf			
Material Condition:	Excellent, New			
Material ID:	Eco 56 Silver			

TESTING METHODS REQUESTED:

Testing Services Inc. was instructed by the client to test for the following				
Standard:	ASTM D1335	Test Method:	Standard Test Method for Tuft Bind Strength of Pile Yarn Floorcoverings	

SAMPLING PLAN:

4/14/2020 Sampling Date:

Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements.

In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager

In the order a special approach the outside environmental conditions of temperature and relative humidity. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested

DEVIATION FROM TEST METHOD:

State reason for any Dev	iation from. Additions to.	or Exclusions From Test Method.
--------------------------	----------------------------	---------------------------------

None

TEST SUMMARY.

TEST METHOD			TEST DESCRIPTION				TEST RESULT			
ASTM D1335-17e1			Average Tuft Bind Strength 10.1 lbs/force							
~	Each individual pull was made on a combination of Monofilament fibers and textured fibers, same needle site									
Pull #1	8.671 lbs/force	Pull #2	9.127 lbs/force	Pull #3	10.26 lbs/force	Pull #4	5.638 lbs/force	Pull #5	15.73 lbs/force	
Pull #6	12.46 lbs/force	Pull#7	10.66 lbs/force	Pull #8	6.685 lbs/force	Pull #9	11.89 lbs/force	Pull#10	9.960 lbs/force	
Pull #11	10.34 lbs/force	Pull #12	8.510 lbs/force	Pull #13	10.26 lbs/force	Pull #14	9.825 lbs/force	Pull #15	10.79 lbs/force	

Uncertainty: We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested.

Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.



TSi Accreditation:

Digitally signed by Erle Miles DN: cn=Erle Miles, o=Testing Services Inc., ou, email=stioffice@optlink.us, c=US Date: 2020.10.30 11:58:31 -0400° All

Erle Miles, III, Lab Director Testing Services (TSI) LLC

Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0 TSi is an Organizational Member of ASTM (American Society for Testing and Materials). TSi is a certified independent testing laboratory by the STC (Synthetic Turf Council).



Page 1 of 1

OUR LETTERS AND REPORTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE OUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. THESE LETTERS AND REPORTS ARE FOR THE USE ONLY OF THE CLIENT TO WHOM THEY ARE ADDRESSED AND THEIR COMMUNICATION TO ANY OTHERS OR THE USE OF THE NAME TESTING SERVICES, INC. MUST RECEIVE OUR PRIOR WRITTEN APPROVAL. OUR REPORTS, LETTERS, NAME, SEALS, OR INSIGNIA ARE NOT UNDER ANY CIRCUMSTANCES TO BE USED IN ADVERTISING TO THE GENERAL PUBLIC.